

LMM-6018 BLACK LASER MARKING TAPE

Technical Information Laser Marking Product

1.0 Product Description

LMM-6018 is a laser marking tape designed for use on stainless steel, glass, ceramic, ceramic like and porcelain substrates. LMM-6018 can be applied to a substrate, laser marked to bond a portion of the tape to the substrate and then peeled away to leave the mark. LMM-6018 is designed for use in applications where spraying and removing our other laser marking materials is not possible or feasible. Rolls are available in 1", 2", 3" and 4" widths. They are 50 feet in length per roll, wound on a standard 3" core. Samples are available in 2" by 6" sheets.

2.0 Product Characteristics

2.1 Physical Properties	
Appearance	Dark black adhesive tape with a white paper backing.
2.2 Strengths of Product	
Raises the contrast of laser marks on steel, glass and ceramic substrates. Allows Nd:YAG, CO2 and fiber lasers to mark substrates such as steel, glass, and porcelain with a dark black mark. Easy to handle and use. Eliminates variation in application, requires no application equipment. Significantly reduces post marking clean up.	
2.3 Recommended Application / Removal Techniques	
Application Methods	Apply LMM-6018 to substrate and smooth out by hand, ensure that no air bubbles or gaps occur between tape and substrate. Moderate pressure should insure good adhesion. LMM-6018 may also be applied by automated machines.
Application Notes	Clean the surface of substrate so that it is free of any lubricants or oils. LMM-6018 must adhere well to the substrate to ensure a consistent mark.
Removal Methods	Remove tape by peeling from surface. Some burned paper residue may need to be wiped away. A cloth can be used with water or ethanol. Some cut out portions of tape may also need removed, depending on the mark.
2.4 Laser Marking of Product	
Laser Marking Method	CO2, YAG or Fiber laser
Recommended Starting Point for Settings	CO2: 100% power (35 watt laser) 5-10% speed, 500 DPI / 500 PPI YAG- 30-50 watts 5-10 inches/sec speed

2.6 Additional Application Notes

For optimum mark quality, good adhesion and contact between the tape and the substrate is necessary. The tape must stick well to the substrate. If gaps or air bubbles are trapped between the tape and the substrate, poor mark quality will result. Use moderate pressure to insure good contact. Use of a squeegee will help insure good contact. Rough or uneven substrates such as porous non-glazed ceramics or bricks will also produce marks of lower resolution due to the roughness of the material.

2.7 Marking Notes

Some burning of the paper backing will occur during marking and is normal. We recommend that the marking be done in a well ventilated area. When making large marks or a large quantity of marks, we recommend a ventilation system to exhaust the smoke created from the paper burning to the outside.

Marking may require some trial and error to optimize your laser with a particular substrate. Keep in mind that all lasers react differently depending on the substrate. Best results are obtained when marking at lower powers and slower speeds. High powers tend to damage glass substrates and should be avoided whenever possible. Experimentation should be done to find settings that produce an acceptable mark without glass damage.

3.0 Product Preparation

No preparation is necessary, use LMM-6018 tape as supplied.

4.0 Storage Recommendations

Product must be stored in cool and dry conditions. Storage temperatures should be between 40°F (5°C) and 95°F (35°C). If stored as recommended, a minimum shelf life of six months after the production date is guaranteed.

IMPORTANT INFORMATION

The following supersedes any provisions in your company's forms, letters and papers. The information and statements contained herein are provided free of charge. They are believed to be accurate at the time of publication. Ferro makes no warranty, whether expressed or implied, including warranties of merchantability or fitness for a particular purpose for these products. No statement or recommendations contained in the product literature are to be construed as inducements to infringe any relevant patent now or hereafter in existence. Under no circumstances shall Ferro be liable for incidental, consequential or other damages from alleged negligence, breach of warranty, strict liability, contract or any other legal theory, arising out of the use or handling of these products. The sole remedy of the buyer and the sole liability of Ferro for any claim shall be for the buyer's purchase price of the products that are the subject of the claim. Claims not made within thirty (30) days from the delivery date shall be deemed waived. Ferro's liability ceases upon making delivery of the product to carrier at shipping point.



Phone: (800) 869-7800 • Email: service@johnsonplastics.com

Connect with us:    