

STONE COLOR FILL UV STABILITY

LaserBits Stone Color Fill materials are tested for lightfastness and UV stability using a nationally recognized testing method.

The American Standard Test Measure (ASTM) gives ratings from I to V.

I is excellent, II very good, III fair or non-permanent in artist's paints, IV and V pigments are rated poor and very poor. (For details, read ASTM D4303-03.)

Below are the ASTM ratings for LaserBits Stone Color Fill:

SUS 196	White	Rating = 1, excellent lightfastness
SUS 197	Blue	Rating = 1, excellent lightfastness
SUS 198	Red	Rating = 2, good lightfastness
SUS 199	Gold	Rating = 1, excellent lightfastness
SUS 200	Silver	Rating = 1, excellent lightfastness
	Black	Rating = 1, excellent lightfastness



JOHNSONPLASTICS
PLUS

Phone: (800) 869-7800 • Email: service@johnsonplastics.com

Connect with us: [f](#) [in](#) [t](#) [v](#)