

15 oz. STAINLESS STEEL MUG

XP8501

Settings

- **Time:** 110 seconds
- **Temperature:** 340 °F
- **Pressure:** Moderate



Tools & Accessories

- Heat Tape
- Mug Press

Fabrication Process

- Affix the transfer to the mug using heat tape.
- Place sacrificial paper over the transfer.
- Place in mug press and press for required time. Pressure knobs are finger tight against product while it is closed in the press.
- After cure time, remove from press and set aside to cool. Water bath can be used for faster cooling.

Note

Use caution when removing from press. Product will be extremely hot.