

STEMLESS STAINLESS STEEL WINE CUPS (17 oz.)

DW25528 – Stainless Steel

DW2W29 – White Stainless Steel

Settings

- Time: 60 seconds
- Temperature: 400° F
- Pressure: Moderate | Heavy

Supplies

- JP Sublimation Paper | Silicone Wrap | HPN Mug Press or Convection Oven

Sublimation Process

- Preheat mug press to 400° F while preparing product.
- Position artwork and use tapered insert w/stopper to press cup. Press using settings noted above.
- If using a **convection oven**, preheat to 400°F while preparing product.
- Use silicone wrap to press transfer onto cup.
- Heat in oven for 6-7 minutes.
- Use protective glove to remove as product will be extremely hot.
- Remove silicone & transfer.

Heat Transfer Process

- Preheat mug press to 320° F while preparing product.
- Use Magic Touch CPM 6.2 paper for transfer.
- Position artwork and use tapered insert w/stopper to press cup.
- Press for 1 to 1.5 minutes with moderate to heavy pressure.
- Peel warm.