

SCREEN PRINTING ON ROWMARK MATERIAL

For screen printing, Rowmark recommends the following inks and settings:

Ink: Nazdar 9700 series

Thinner: Nazdar RE 180

Ink Mix: 10:1 ink to thinner ratio

Mix ink and thinner well and apply to plastic. Allow to cure 24-36 hours at room temperature. For information on forced drying, see Nazdar's technical information on the following pages.

Rowmark materials recommended for screen-printing:

| | |
|----------------------------|---------------------------------|
| ADA Alternative | Satins |
| ColorCast Acrylics | Slickers |
| Earthtones | Silks |
| FlexiBrass® & FlexiColor® | Standard Metals |
| Granites Deluxe™ | Textures |
| Lacquers | LaserMark® |
| LaserMax® | Mattes |
| Outdoor Weatherable Metals | NoMark® Plus |
| Reverse LaserMark® | Ultra-Mattes Reverse Engravable |

Refer to Nazdar's technical data documentation on their 9700 series inks within the above products' folders on Rowmark technical help.

* **Note** – Rowmark is not affiliated with and does not receive any compensation from Nazdar and provides this recommendation only as a courtesy to our customers.